

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Australian Select Timbers Pty Ltd
136 Atlas Boulevard
Dandenong South VIC 3175

Test Number : 24-001573
Issue Date : 17/05/2024
Print Date : 17/05/2024

Sample Description Clients Ref : "Reflections 8mm Laminate with 2mm Underlay"
Laminate flooring plank tested on foam underlay
Colour : Timber look
End Use : Flooring
Nominal Composition : High density fibreboard, EVA foam underlay
Nominal Mass per Unit Area/Density : Plank 880kg/m³ Underlay Approx: 110kg/m³
Nominal Thickness : 10mm



321647

70470

Page 1 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Australian Select Timbers Pty Ltd
136 Atlas Boulevard
Dandenong South VIC 3175

Test Number : 24-001573
Issue Date : 17/05/2024
Print Date : 17/05/2024

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 06-05-2024

Date Tested 17-05-2024

CHF Value	1	2	3	Mean
Length	6.4	6.2	6.4	6.3 kW/m ²
Width	10.6	-	-	- kW/m ²
HF-30 Value	1	2	3	Mean
Length	8.0	6.2	6.4	6.9 kW/m ²
Width	-	-	-	- kW/m ²
Smoke Value	1	2	3	Mean
Length	66	26	12	35 %.min
Width	16	-	-	- %.min

321647

70470

Page 2 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Australian Select Timbers Pty Ltd
136 Atlas Boulevard
Dandenong South VIC 3175

Test Number : 24-001573
Issue Date : 17/05/2024
Print Date : 17/05/2024

Observation

Blistering

Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was loose laid over EVA 2mm Foam Underlay and 6mm thick fibre reinforced cement board and clamped prior to testing.

321647

70470

Page 3 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR