



## DRY FLOOR FRICTION SLIP RESISTANCE TEST

### Artistry Collection - Insignia Oak

**Prepared for:** Australian Select Timbers  
136 Atlas Boulevard  
DANDENONG SOUTH VIC 3175

**Specimen Description:** Artistry Collection - Insignia Oak, 150x1050 mm.

**No. of Specimens:** 2 off (Sampling Conducted by Client)

**Specimen Preparation:** Washed with water and pH neutral detergent, rinsed then dried.

**Test Condition & Slope:** Unfixed, N/A

**Test Direction:** Test conducted parallel with grain of timber.

**Air Temperature:** 22°C

**Test Standard:** AS 4586:2013 Slip resistance classification of new pedestrian surface materials, Appendix B - Dry Floor Friction Test

**Test Location:** ATTAR 44-48 Rocco Drive, Scoresby, VIC, 3179

**Test Date:** 13 December 2022

**Test Equipment:** Tortus Floor Friction Tester Mk III, Serial Number 318

**Slider Rubber:** Slider 96 Batch No. #12 prepared on P400 SiC paper.

**Test Personnel:** Dale Siegle

Coefficient of Friction (COF):	Run 1	Run 2
		0.67
<b>Mean COF (rounded to 0.05)</b>	<b>0.70</b>	
<b>Classification:</b>	<b>D1</b>	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked.

Prepared by:




Dale Siegle  
Technical Consultant - Compliance Services  
Approved Signatory

Reviewed By:



Marcus Braché  
Senior Engineering Technician  
Approved Signatory



**Figure 1:** Artistry Collection - Insignia Oak  
Arrow indicates direction of testing



**CLASSIFICATION CRITERIA – AS 4586: 2013**  
**Dry Floor Friction Test - Appendix B**

**Slip resistance**

The 'dry floor friction' test method in Appendix B is not suitable for heavily profiled surfaces or carpets.

**Compliance**

The surface shall comply with the stated classification for the test method that is nominated and declared by the manufacturer or supplier.

**TABLE 3: CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS  
ACCORDING TO THE AS 4586 DRY FLOOR FRICTION TEST**

<b>Classification</b>	<b>Floor friction tester mean value</b>
D1	≥0.40
D0	<0.40

**Means of demonstrating compliance**

Pedestrian surfaces that are classified in accordance with Table 3 where appropriate, shall meet the following criteria:

- (a) The mean test results shall be as follows:
  - (i) For Classification D1 in Table 3—
    - (A) the mean of the test results shall be equal to or greater than 0.4; and
    - (B) each individual slope corrected result shall be equal to or greater than 0.35.

If either of these criteria is not met, the lot shall be considered to be Classification D0.
- (b) The classification in accordance with Table 3 shall be determined by—
  - (i) selecting and testing specimens at random as specified in Appendix B of AS4586; or
  - (ii) carrying out continuous testing and process control in accordance with AS 3942.
- (c) When testing individual lots, if a particular test fails to produce the expected classification it shall be permissible to—
  - (i) disregard the first sample, resample a minimum of 10 specimens from the whole lot, retest and apply the criteria to the new sample; or
  - (ii) subdivide the lot into smaller lots of different quality, resample, retest and reclassify each of the smaller lots.