# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client: Australian Select Timbers Pty Ltd

136 Atlas Boulevard

Dandenong South VIC 3175

Test Number : 25-002682 Issue Date : 8/08/2025

Issue Date : 8/08/2025

Print Date : 11/08/2025

Sample Description Clients Ref : "Montvale American Oak"

Engineered timber flooring planks

End Use: Flooring

Nominal Composition: 1mm American Oak Veneer, 7 layer multiply core

Nominal Mass per Unit Area/Density: 680kg/m3

Nominal Thickness: 14mm



355893 78127 Page 1 of 3

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hons)

Fiona McDonald

APPROVED SIGNATORY

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

### **TEST REPORT**

Client: Australian Select Timbers Pty Ltd

136 Atlas Boulevard

Dandenong South VIC 3175

Test Number: 25-002682 Issue Date 8/08/2025

**Print Date** 11/08/2025

AS ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

**Radiant Heat Source** 

Date of Sample Arrival

10-07-2025

**Date Tested** 

08-08-2025

| CHF Value | 1   |
|-----------|-----|
| Length    | 6.3 |
| Width     | 4.3 |

3 4.3 4.4 Mean kW/m<sup>2</sup> 4.3 kW/m<sup>2</sup>

HF-30 Value

1

Mean

Length Width

Length

Width

6.3 4.4

2 4.3

4.4

kW/m<sup>2</sup> 4.4 kW/m<sup>2</sup>

Smoke Value

1 9

17

2 15

3 15

3

Mean %.min %.min

16

355893

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

78127

Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

> Fiona McDonald APPROVED SIGNATORY

A. JACKSON B.Sc.(Hons) MANAGING DIRECTOR

Page 2 of 3

0204/11/06



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

### **TEST REPORT**

Client: Australian Select Timbers Pty Ltd

136 Atlas Boulevard

Dandenong South VIC 3175

**Test Number** : 25-002682

Issue Date : 8/08/2025
Print Date : 11/08/2025

Observation

Blistering

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

355893 78127 Page 3 of 3

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hons)