

## Formaldehyde Emission Test Certificate

Monday February 7<sup>th</sup>, 2022

Supplier: Australian Select Timber (61-63 Discovery Road, Dandenong, VIC, 3175, Australia)

Sample Description: Opulence Native Collection

Date Tested: December 2021 (Tested through FORAY Laboratories - NATA Accreditation 1231)

Test Method: ASTM D5116-17 "Standard Guide for Small-Scale Environmental Chamber Determinations of Organic Emissions from Indoor Materials/Products".

Emission Data (7 days exposure):

<b>Green Building Council of Australia</b> Green Star Design & As Built v1.3 13.1.2B & 13.2 Green Star Interiors V1.3 - 12.1.2B	<b>Opulence Native Collection</b>
Formaldehyde Emission Rate limit: ≤0.1 mg/m²/hr	Formaldehyde Emission Rate: 0.063 mg/m²/hr

Dr. Vyt Garnys PhD, BSc(Hons) AIMM, ARACI, ISIAQ ACA, AIRAH, FMA Managing Director and Principal Consultant

Luke Morley BSc (Technology) Consultant

TOUR

Dr. Tuan Duong PhD, B Eng. (Chem.) Senior Consultant

Technology & Innovation