



Technical Data Sheet

GrandOak Noble Collection

Ge	ne	ral	Inf	orn	nati	on
$\overline{}$				O	1100	U ::

Size	1900mm x 190mm
Thickness	14.5mm
Gloss Level	20% Gloss Level Wire Brushed Matte Finish Smooth Finish Hand Scraped
Surface Coating	UV Lacquer 8-10 Coats
Top Layer (Veneer)	3mm European Oak
Origin of Timber Veneer	Europe
Janka hardness rating	1360 LBF (7.0)
Profile	Engineered Tongue & Groove
Pattern	Single Strip
Structure	8 layer multi-ply core, timber surface veneer
Edging	Bevelled Edging
Pack Coverage	2.166m²
Pack Weight	21kg
Pack Length	1900mm, 6 boards per pack - All full lengths
Pallet Packs	55
Application	Residential & Commercial
Environmental Rating	Δ+
Maintenance	As per Australian Select Timbers – GrandOak's care & maintenance instructions - please refer to: asttimbers.com.au

Accessories

Matching Colour Stair Nosing	1890 x 90 x 14.5mm (Engineered timber)
Stair Nosing's Profile	Square Edge
Matching Colour Scotia	1900 x 18 x 18mm (Solid timber)
C-Channel Adjustable Height Aluminium Trims	3400 x 22 x 12-15mm (Available in Black, Champagne, Silver, & other Wooden Colours)
H-Channel Adjustable Height Aluminium Trims	3400 x 38 x 12-15mm (Available in Black, Champagne, Silver, & other Wooden Colours)



Technical Data Sheet

GrandOak Noble Collection

Installation

Fully Bonded	Yes*
Nailed	No
Floated on underlay	Yes*
Over Hydronic Heated Slab*	Yes*

^{*}Please refer to our Installation Instructions and Heated Slab Installation Instructions for more information.

Grading Specifications

Timber Grade	Classic
Colour Variation	Allowed
Filled Defects	Allowed
Sapwood	Max 10% width
Black/Coloured Filler	Will be present (Allowed)
Maximum size of knots	40mm diameter (Will be present)
Heart/Pith	Trace
End Checks	Filled
Insect Damage	Filled
Ingrown Bark	Not Allowed

GrandOak Noble Collection is made of European Oak. As a natural timber product, knots will be present, as well as the use of black and/or coloured fillers. Colour variation and grain are to be expected and will also vary on the floorboards. These variations will occur from batch to batch, between samples and the actual stock delivered and installed. These variations are normally present in the GrandOak Noble Collection and are not considered defects. Furthermore, it will not form the basis of any claims under the warranty.

Filled defects and trace amounts of the heartwood are present in this grade.

This Classic grade of timber is the most common standard and widely used in the timber industry.

Timber flooring is not colour-fast, and the colour will change over time when exposed to UV light. Surface checking may be present.

Test Results & Certificates'

Acoustic Result* L'nT, w: 43 (5 Star - AAAC Star Rating) Legally harvested timber Yes FSC Available upon request Thermal Test ASTM C518-2017 Thermal Resistance (R Value) Result: 0.155 m²k/w (with 2mm Select Underlay) Wet Slip Test AS 4586:2013 Classification: P3 Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003 Result CRF 4.4 kw/m²		
Legally harvested timber FSC Available upon request Thermal Test ASTM C518-2017 Thermal Resistance (R Value) Result: 0.155 m²k/w (with 2mm Select Underlay) Wet Slip Test AS 4586:2013 Classification: P3 Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003	Acoustic Result*	=,
FSC Available upon request Thermal Test ASTM C518-2017 Thermal Resistance (R Value) Result: 0.155 m²k/w (with 2mm Select Underlay) Wet Slip Test AS 4586:2013 Classification: P3 Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003		(5 Star - AAAC Star Rating)
Thermal Test ASTM C518-2017 Thermal Resistance (R Value) Result: 0.155 m²k/w (with 2mm Select Underlay) AS 4586:2013 Classification: P3 Classification: D1 Australian Reaction to fire - ASISO 9239:1-2003	Legally harvested timber	Yes
Thermal Resistance (R Value) Result: 0.155 m²k/w (with 2mm Select Underlay) Wet Slip Test AS 4586:2013 Classification: P3 Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003	FSC	Available upon request
Result: 0.155 m²k/w	Thermal Test	ASTM C518-2017
(with 2mm Select Underlay) Wet Slip Test AS 4586:2013 Classification: P3 Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003		Thermal Resistance (R Value)
Wet Slip Test AS 4586:2013 Classification: P3 Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003		Result: 0.155 m ² k/w
Classification: P3 Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003		(with 2mm Select Underlay)
Dry Slip Test AS 4586:2013 Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003	Wet Slip Test	AS 4586:2013
Classification: D1 Australian Reaction to fire - ASISO 9239.1-2003		Classification: P3
Australian Reaction to fire - ASISO 9239.1-2003	Dry Slip Test	AS 4586:2013
		Classification: D1
FLOOR Result CRF 4.4 kw/m ²	Australian Reaction to fire -	ASISO 9239.1-2003
	FLOOR	Result CRF 4.4 kw/m ²
Smoke value 35%		Smoke value 35%
Australian Reaction to fire - AS/NZS 3837:1998	Australian Reaction to fire -	AS/NZS 3837:1998
WALL Result: 54.1kw/m ²	WALL	Result: 54.1kw/m ²
Release of formaldehyde ASTM D5116 Result 0.011mg/m²/hr	Release of formaldehyde	ASTM D5116 Result 0.011mg/m ² /hr
(max allowable 0.1)		(max allowable 0.1)
Release of ASTM D5116 Result 0.003mg/m²/hr	Release of	ASTM D5116 Result 0.003mg/m ² /hr
4-phenylcyclohexene (max allowable 0.05)	4-phenylcyclohexene	(max allowable 0.05)
Total VOC ASTM D5116 Result 0.046mg/m²/hr	Total VOC	ASTM D5116 Result 0.046mg/m ² /hr
(max allowable 0.5)		(max allowable 0.5)

'All test reports and certificates are available upon request. Acoustic test results are site specific (will vary from building to building), and as such, the above result is indicative only. Prior to purchase, Australian Select Timbers recommends carrying out an independent acoustic test for a site specific result.

Test conducted on site as a floating floor with the use of 2mm and 3mm Select EVA Underlay. Please contact Australian Select Timbers for further information regarding these test results.

Warranties

Warranty - Residential	20 Year Wear & Lifetime Structural		
Warranty - Commercial	10 Year Wear & Lifetime Structural		







Installation & Warranty

All GrandOak floors must be installed by a competent approved installer who has all the necessary skills and take individual site circumstance into account. GrandOak's warranty will only apply to floors which have been installed according to the GrandOak's installation instructions available in each pack and also on the GrandOak's website – **grandoakflooring.com.au**

Terms & Conditions: Please note this technical sheet was written by Australian Select Timbers Pty Ltd. All the information is specified correctly while writing and publication of the sheet. The company reserves the right to change the specifications of this product at any time without prior notice to third parties.

Colour Disclaimer: We cannot guarantee that the colours you see printed on this technical data sheet or displayed on our website accurately portrays the true colours of the floorboards. Electrical device's monitors and/or screens are not calibrated equally and colour reproduction on the Internet is not precise. Swatch colours can be verified by ordering a complimentary offcut sample from our website or visiting an Australian Select Timbers' retail partner to view in-store.

Australian Select Timbers Pty Ltd.

^{*}All testing conducted on 200mm concrete slab and a single layer of 10mm standard suspended plasterboard ceiling (with no insulation) as per B.C.A and AAAC requirements.