





DRY FLOOR FRICTION SLIP RESISTANCE TEST

LVT Symphony 2.5mm Vinyl Plank

Prepared for: Australian Select Timbers

136 Atlas Boulevard

DANDENONG SOUTH VIC 3164

Sample Description: LVT Symphony 2.5mm Vinyl Plank

No. of Specimens &

Size Supplied: 1 off , 177x999 mm, (Sampling Conducted by Client)

Specimen Preparation: Washed with water and pH neutral detergent, rinsed then dried.

Test Condition & Slope: Unfixed, N/A

Test Direction: Test conducted parallel with embossed finish.

Air Temperature: 22°C

Test Standard: AS 4586:2013 Slip resistance classification of new pedestrian surface

materials, Appendix B - Dry Floor Friction Test

Test Location: ATTAR 44-48 Rocco Drive, Scoresby, VIC, 3179

Test Date: 9 April 2024

Test Equipment: Tortus Floor Friction Tester Mk III, Serial Number 318 **Slider Rubber:** Slider 96 Batch No. #24 prepared on P400 SiC paper.

Test Personnel: Marcus Bosworth

Coefficient of Friction (COF):	Run 1	Run 2
	0.74	0.76
Mean COF (rounded to 0.05)	0.75	
Classification:	D1	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked.

Prepared by:

Marcus Bosworth

Compliance and Testing Technician

Reviewed By:

Daniel King BSc/BEng (mat) Hons., MIEAust General Manager - Compliance Services

Approved Signatory

This report may not be reproduced except in its entirety.






Figure 1: LVT Symphony 2.5mm Vinyl Plank Arrow indicates direction of testing



CLASSIFICATION CRITERIA – AS 4586: 2013 Dry Floor Friction Test - Appendix B

Slip resistance

The 'dry floor friction' test method in Appendix B is not suitable for heavily profiled surfaces or carpets.

Compliance

The surface shall comply with the stated classification for the test method that is nominated and declared by the manufacturer or supplier.

TABLE 3: CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS ACCORDING TO THE AS 4586 DRY FLOOR FRICTION TEST

Classification	Floor friction tester mean value
D1	≥0.40
D0	<0.40

Means of demonstrating compliance

Pedestrian surfaces that are classified in accordance with Table 3 where appropriate, shall meet the following criteria:

- (a) The mean test results shall be as follows:
 - (i) For Classification D1 in Table 3—
 - (A) the mean of the test results shall be equal to or greater than 0.4; and
 - (B) each individual slope corrected result shall be equal to or greater than 0.35.

If either of these criteria is not met, the lot shall be considered to be Classification D0.

- (b) The classification in accordance with Table 3 shall be determined by—
 - (i) selecting and testing specimens at random as specified in Appendix B of AS4586; or
 - (ii) carrying out continuous testing and process control in accordance with AS 3942.
- (c) When testing individual lots, if a particular test fails to produce the expected classification it shall be permissible to—
 - (i) disregard the first sample, resample a minimum of 10 specimens from the whole lot, retest and apply the criteria to the new sample; or
 - subdivide the lot into smaller lots of different quality, resample, retest and reclassify each of the smaller lots.