

This report is a replacement of Report No. 22281.1 This version incorporates an alternative name used for the same product at the request of the client.





WET PENDULUM SLIP RESISTANCE TEST

LVT Symphony 4.5mm vinyl plank stair tread

Prepared for: Australian Select Timbers

136 Atlas Boulevard

DANDENONG SOUTH VIC 3175

Sample Description: LVT Symphony 4.5mm vinyl plank stair tread

No. of Specimens &

Size Supplied:

5 off, 150x150 mm, (Sampling Conducted by Client)

Specimen Preparation: Washed with water and pH neutral detergent, rinsed then dried.

Test Condition & Slope: Unfixed, N/A

Test Direction: Test conducted in the direction of stair descent.

Air Temperature: 22°C

Test Standard: AS 4586:2013 Slip resistance classification of new pedestrian surface

materials, Appendix A - Wet Pendulum Test

Test Location: ATTAR 44-48 Rocco Drive, Scoresby, VIC, 3179

13 March 2025 **Test Date:**

Test Equipment: Munro Stanley Pendulum Skid Resistance Tester Serial Number

0320, Calibrated 05/09/2024.

Slider Rubber: Slider 96 Batch No. #49 prepared on P400 & 3µm lapping film.

Test Personnel: Louie Karkatzoulis

Specimen Number	1	2	3	4	5
Mean British Pendulum Number (BPN)	33	32	31	37	28
Slip Resistance Value (SRV)			32		
Classification		P2+			

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked. Where alternatives are permitted by the standard, the choice of rubber slider used may also influence the test results obtained.

*Testing of this product has been conducted in the direction of pedestrian movement on stair descent per the requirements of AS 4586 Section A6.3.1 (e). This report should only be used for stairway applications. If this product is used in locations other than stairways, a different test direction may be required which could change the SRV and Classification test results.

Prepared By:

Louie Karkatzoulis

Compliance and Testing Technician

Reviewed By:

Dale Siegle

Technical Consultant - Compliance Services

Approved Signatory






Figure 1: LVT Symphony 4.5mm vinyl plank stair tread Arrow indicates direction of testing



CLASSIFICATION CRITERIA – AS 4586 – 2013 Wet Pendulum Test - Appendix A

Slip resistance

When this Standard is used for the testing and classification of the slip resistance of carpets (or carpet-like products) in potentially wet locations, the carpet shall be tested using the wet pendulum test method set out in Appendix A of AS 4586, and shall be reported as such.

When this AS 4586 is used for the testing and classification of the slip resistance of carpets in dry locations, the test shall be carried out in the dry condition using the pendulum test method set out in Appendix A of AS 4586, modified in accordance with Paragraph A2, and shall be reported as such.

The 'dry floor friction' test method in Appendix B of AS 4586 is not suitable for heavily profiled surfaces or carpets.

Compliance

The surface shall comply with the stated classification for the test method and test rubber that is nominated and declared by the manufacturer or supplier.

TABLE 2: CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS ACCORDING TO THE AS 4586 WET PENDULUM TEST

Class	Pendulum SRV (see Note 1)			
	Slider 96	Slider 55		
P5	>54	>44		
P4	45-54	40-44		
P3	35-44	35-39		
P2	25-34	20-34		
P1	12-24	<20		
P0	<12			

NOTES:

- 1 While Slider 96 or Slider 55 rubbers may be used, the test report shall specify the rubber that was used.
- 2 It is expected that these surfaces will have greater slip resistance when dry.
- 3 SDV may be calculated by using the tables that are given in Appendix F of AS 4586, and the minimum SRV that is considered appropriate for a level surface (see examples given in Appendix F of AS 4586).

Means of demonstrating compliance

Pedestrian surfaces that are classified in accordance with Table 2 shall meet the following criteria:

- (a) The mean test results shall be as follows:
 - (i) For the classifications in Table 2, the mean of the test results shall be—
 - (A) within the relevant criteria set out in the table; and
 - (B) each individual result shall be equal to or above the lower limit for the classification or, if below the classification, within the mean of the result minus 20%.

If either criteria is not met, the lot shall be considered to be of lower classification.

- (b) The classification in accordance with Table 2 shall be determined by
 - selecting and testing at least five specimens at random as specified in Appendices A and B of AS 4586; or
 - (ii) carrying out continuous testing and process control in accordance with AS 3942.
- (c) When testing individual lots, if a particular test fails to produce the expected classification it shall be permissible to—
 - disregard the first sample, resample a minimum of 10 specimens from the whole lot, retest and apply the criteria to the new sample; or
 - (ii) subdivide the lot into smaller lots of different quality, resample, retest and reclassify each of the smaller lots.